

SLIPTTEST AUSTRALIA PTY LTD ~ ABN 80 111 154 324 12 Blackburn Court ELANORA QLD 4221 PH 0418 75 3311											
SLIP RESISTANCE CLASSIFICATION OF NEW PEDESTRIAN SURFACE MATERIALS AS 4586 (2013) "Appendix A" (Wet Pendulum Method)											
Report Prepared For:		DISTINCTIVE TILE IMPORTS (DTI)		Client Address:		485 ZILLMERE ROAD ZILLMERE QLD 4034					
Project:		VITRA 30 x 30 781466 Dotti Ivory Mercato BP27									
Property Tested:		VITRA 30 x 30 781466 Dotti Ivory Mercato BP27		Date Tested:		02.02.16		Test Report No:		KO020216-12	
Testing was carried out using the Wet Test Method, using Slider 96 (4S) rubber slider, in accordance with Australian Standard AS 4586 Appendix A Slider was conditioned/prepared using P400 abrasive paper and 3 µm lapping film											
Number of sites tested		5		Classification of Pedestrian surface materials according to the AS 4586 wet pendulum test							
Test location				Comments							
Tile 1		1		Surface Type		Surface Gradient Degrees		Type and extent of Cleaning Performed		Results of last three swings British Pendulum Number	
Tile 2		2		TILE		<1.5		Water & Scrubbing		50 50 50	
Tile 3		3		TILE		<1.5		Water & Scrubbing		50 50 50	
Tile 4		4		TILE		<1.5		Water & Scrubbing		50 50 50	
Tile 5		5		TILE		<1.5		Water & Scrubbing		50 50 50	
Temperature:		31 °C		Mean BPN Slip Resistance Value (SRV)		51		The above classification is provided without Slope Correction Values			
Weather:		Indoors		Mean BPN Slip Resistance Value (SRV)		51		The above classification is provided without Slope Correction Values			
Testing Instrument: Munro Portable Skid Tester # 1133 Calibration Date: 24.08.15 Testing Officer & Signatory: KATHRYN ORDING Fixed Test: Testing is performed in the anticipated direction of pedestrian travel Unfixed Test: Testing is performed in the direction of least anticipated slip resistance Notes:											
Sliptest Australia Pty Ltd Materials Testing Laboratory - Accreditation number 15374 12 Blackburn Court ELANORA QLD 4221 Accredited for compliance with ISO/IEC 17025. The results of the tests, calibrations and/or measurements included in this document are traceable to Australian/National standards. 											