

SLIPTTEST AUSTRALIA PTY LTD ~ ABN 80 111 154 324 12 Blackburn Court ELANORA QLD 4221 PH 0418 75 3311											
SLIP RESISTANCE CLASSIFICATION OF NEW PEDESTRIAN SURFACE MATERIALS AS 4586 (2013) "Appendix A" (Wet Pendulum Method)											
Report Prepared For:		Distinctive Tile Imports		Client Address:		485 Zillmere Road, Zillmere QLD 4034					
Project:		Vltra 30x30 - 751645, Uni Ivory R10, VL17									
Property Tested:		485 Zillmere Road, Zillmere QLD 4034		Date Tested:		1/02/2016		Test Report No:		AO0102162	
Testing was carried out using the Wet Test Method, using Slider 96 (4S) rubber slider, in accordance with Australian Standard AS 4586 Appendix A. Slider was conditioned/prepared using P400 abrasive paper and 3 µm lapping film											
Number of sites tested		5		Results of last three swings		Mean BPN Test		Slope Correction value (SCV)		Classification of Pedestrian surface materials according to the AS 4586 wet pendulum test	
Test location		Surface Type		Surface Gradient Degrees		Type and extent of Cleaning Performed		Results of last three swings British Pendulum Number		Comments	
Tile 1		1		<1.5		Water & Scrubbing		54 54 54		N/A	
Tile 2		2		<1.5		Water & Scrubbing		54 54 54		N/A	
Tile 3		3		<1.5		Water & Scrubbing		55 55 55		N/A	
Tile 4		4		<1.5		Water & Scrubbing		54 54 54		N/A	
Tile 5		5		<1.5		Water & Scrubbing		53 53 53		N/A	
Temperature:		28 °C		Mean BPN Slip Resistance Value (SRV)		54		The above classification is provided without Slope Correction Values			
Weather:		Indoors									
Testing Instrument: Wessex Portable Skid Tester # 1913 Calibration Date: 14.10.14				Sliptest Australia Pty Ltd							
Testing Officer & Signatory: ADAM OLIVER				Materials Testing Laboratory - Accreditation number 15374							
Fixed Test: Testing is performed in the anticipated direction of pedestrian travel				12 Blackburn Court ELANORA QLD 4221							
Unfixed Test: Testing is performed in the direction of least anticipated slip resistance				Accredited for compliance with ISO/IEC 17025. The results of the tests, calibrations and/or measurements included in this document are traceable to Australian/National standards.							
Notes:											

